

SPECIFICATION

BITUMEN

60/70



| PROPERTIES | RESULT | TEST METHOD |
|---------------------------|-----------|-----------------|
| Specific gravity@25/25 °C | 1.01 - 16 | ASTM D70 |
| Penetration@25 °C, 5 | 60 - 70 | ASTM D5 |
| Softening point °C | 49.56 | ASTM D36 |
| Ductility@25 °C | 100 min | ASTM D113 |
| Loss on heating (wt%) | 0.2 max | ASTM D6 |
| Drop-in penetration | 20 max | ASTM D6 & D5 |
| Flash point | 250 min | ASTM D92 |
| Solubility in C2 (wt%) | 99.5 min | ASTM D4 |
| Spot test | Negative | A.A.S.H.O.T 102 |

The analysis will be customizable & produce able as per buyer's request